

Partex Heatshrink Tubing Kits. 2:1 Ratio Single wall.

HS KIT1 - CONTAINS: BLACK, BLUE, GREY, BROWN AND EARTH.



| PART REF: | SIZE (mm) | CONTENTS |
|--------------|-----------|--|
| HS KIT1 3.2 | 3.2/1.6 | Contains 3 X 250mm lengths of each colour. |
| HS KIT1 4.8 | 4.8/2.4 | Contains 3 X 250mm lengths of each colour. |
| HS KIT1 6.4 | 6.4/3.2 | Contains 3 X 250mm lengths of each colour. |
| HS KIT1 9.5 | 9.5/4.7 | Contains 3 X 250mm lengths of each colour. |
| HS KIT1 12.7 | 12.7/6.3 | Contains 3 X 250mm lengths of each colour. |
| HS KIT1 19.1 | 19.1/9.5 | Contains 2 X 250mm lengths of each colour. |
| HS KIT1 25.4 | 25.4/12.7 | Contains 2 X 250mm lengths of each colour. |
| HS KIT1 38.1 | 38.1/19.0 | Contains 2 X 250mm lengths of each colour. |

HS KIT2 - CONTAINS: RED, YELLOW, GREEN, BLACK, BLUE, GREY, BROWN, WHITE, CLEAR AND EARTH.



| PART REF: | SIZE (mm) | CONTENTS |
|--------------|-----------|--|
| HS KIT2 3.2 | 3.2/1.6 | Contains 2 X 250mm lengths of each colour. |
| HS KIT2 4.8 | 4.8/2.4 | Contains 2 X 250mm lengths of each colour. |
| HS KIT2 6.4 | 6.4/3.2 | Contains 2 X 250mm lengths of each colour. |
| HS KIT2 9.5 | 9.5/4.7 | Contains 2 X 250mm lengths of each colour. |
| HS KIT2 12.7 | 12.7/6.3 | Contains 2 X 250mm lengths of each colour. |
| HS KIT2 19.1 | 19.1/9.5 | Contains 2 X 250mm lengths of each colour. |
| HS KIT2 25.4 | 25.4/12.7 | Contains 2 X 250mm lengths of each colour. |
| HS KIT2 38.1 | 38.1/19.0 | Contains 2 X 250mm lengths of each colour. |

Supplied in sturdy Polythene bags with a Euro slot.

| | | | |
|-----------------------|-------------------------------|--------------------|-------------|
| MATERIAL | Polyolefin (Crosslinked) | STANDARD | UL224 125°C |
| FEATURE | Flame Retardant, Zero Halogen | SHRINK TEMP | 90-100°C |
| VOLTAGE | 600 V | WORK TEMP | -55°C-125°C |
| FLAME PROPERTY | Halogen free. | WALL TYPE | Single |

| PROPERTY | DATA | CONDITION |
|------------------------------|-----------------------|---------------------|
| Tensile Strength | >10.4MPa | |
| Tensile Strength After Aging | >7.3MPa | 158.0±1.0°C, 168hrs |
| Elongation | >200% | |
| Elongation After Aging | >100% | 134°C 60 days |
| Longitudinal Change | <±5% | |
| Radial Shrinking Ratio | >50% | |
| Flammability | VW-1 | |
| Dielectric Strength | >15kV/mm | |
| Volume Resistivity | 10 ¹⁴ W-cm | |
| Corrosion | No Corrosion | |
| Copper Stability | >100% | |
| Concentricity | >65% | |

